

Objekt

Deep matt isolating acrylate paint



- ✓ Reinforced with synthetic resin
- ✓ Isolates dirt efficiently
- ✓ Excellent adhesion to a variety of substrates



Description	
Properties	<p>Acrylate water-borne paint for badly fouled surfaces in rooms with high service load.</p> <ul style="list-style-type: none"> ✓ Isolates nicotine, smoke, soot and rust stains, water and similar stains well. ✓ Repaints badly fouled surfaces well, providing an absolutely matt dense coating. ✓ Good opacity. ✓ High adhesion to a variety of substrates, including the surfaces painted with alkyd and oil-base paints. ✓ Reinforced with synthetic resin ✓ Is especially suitable for urgent repair works ✓ Can be tinted into over 10,000 colours <p>Maximum permissible EU VOC content for the product (subcat i) 140 g/L. Maximum VOC content in the product ≤140 g/L.</p> <p>Gloss:</p> <ul style="list-style-type: none"> ✓ deep matt (approximately 2) in accordance with EN 13300; ✓ deep matt (approximately 2) in accordance with ISO 2813; <p>Wash resistance:</p> <ul style="list-style-type: none"> ✓ class 3 in accordance with EN 13300 (ISO 11998);
Purpose	<p>Intended for repainting badly fouled surfaces in apartment building stairwells, staircases, corridors, hotels, kitchen ceilings.</p> <p>Suits well as a primer to be used under water-borne paints.</p>
Types of surfaces for painting	<p>Surfaces previously painted with water-borne, alkyd or oil-base paints or new surfaces made of concrete, aerated concrete, gypsum board; brick; surfaces finished with putty or plastered. For indoor use.</p>
Quality standards and labels	<ul style="list-style-type: none"> ✓ EN 13300 [Paints and varnishes. Water-borne coating materials and coating systems for interior walls and ceilings. Classification] – classification standards of coverage, gloss level and wet abrasion resistance parameters for water-borne coating materials for interior walls and ceilings. ✓ ISO 11 998 [Paints and varnishes -- Determination of wet-scrub resistance and cleanability of coatings], ISO 2813 [Paints and varnishes -- Determination of specular gloss of non-metallic paint films at 20 degrees, 60 degrees and 85 degrees] – techniques for measuring gloss and wear resistance parameters. ✓ VOC (volatile organic compounds) – content in accordance with the European Union directive 2004/42/CE. ✓ Product and service quality is guaranteed by the quality, environmental protection, occupational health

	and safety management system in accordance with standards ISO 9001:2015; ISO 14001:2015 and OHSAS 18001:2007.
Product specifications	
Surface preparation before painting	The surface to be painted must be carefully cleaned from peeling material, dirt and dust. Fill cracks and dents with suitable putty (Fine Filler, Aqua Filler etc.). We recommend you to wash the surface with a 3–5% solution of soda or a detergent containing ammonia solution, rinse it with water and dry before painting. The surfaces that get wet so often that mould can develop there must be treated with Biotol E before painting. The surfaces newly finished with putty should be primed with the Aquastop or Tiefgrund moisture barrier. Follow the product instructions for use.
Application	Stir the paint thoroughly before application. The paint can be diluted with water in the amount of up to 5% of its volume for the application of the first coat. Apply 2 coats with a roller or spray gun at the temperature between 10°C and 25 °C and relative humidity not exceeding 80%. Avoid application in draughty places and at high air temperature (over +25°C). When painting, make sure to keep a wet edge.
Care for the painted surface	The product achieves its final hardness and durability after one month under normal conditions; therefore the surfaces must be handled with care during this time. If necessary, the surface can be lightly wiped with a soft sponge or cloth approximately 48 hours after paint application. We recommend using water and neutral or medium alkaline detergents (pH below 9). Do not use solvents, abrasive cleansers and hard scrubbing brushes or sponges. Extensive rubbing may make the surface glossy. We recommend using Biotol E and Biotol Spray to remove mould.
Colour	White.
Tinting	Machine tinting according to the Eskarocolor system (bases A).
Consumption	6-10 m ² /L.
Thinner	Water
Drying time	At the temperature of +20 °C and the relative humidity of 50%, the surface is ready for the application of another coat in 1–1.5 hours and is fully dry in 2 hours.
Tools	Roller, brush.
Tool cleaning	Wash with soap and water after completing work.
Additional information	
Frost resistance	None.
Min shelf life	3 years
Storage conditions	Store and transport in tightly sealed containers at the temperature between +5 °C and +30 °C. Protect from exposure to freezing and direct sunlight.
Safety precautions	The product is not classified as dangerous according to CLP Regulation (EC) n° 1272/2008. Keep out of reach of children. Do not eat or drink during the process, washing hands afterwards with suitable cleaning products. In case of paint contact with eyes, wash the eyes with plenty of water. As a preventative measure it is recommended to use basic Personal Protection Equipment.
Waste treatment	Avoid release to the environment. Dispose of the contents/containers in accordance with the current legislation on waste treatment. Waste treatment methods: code 08 01 12- Waste paint and varnish other than those mentioned in 08 01 11, waste class (Regulation (EU) No 1357/2014): non-dangerous.
Density	1,4 kg/L.
Volume/weight:	0,9 L – 2,7 L –9L
The information concerning the product is based on the results of laboratory tests and practical use of the product depending on the location and conditions of its use. As the manufacturer, we guarantee the quality of the product and provide the best recommendations for its appropriate application. As the manufacturer, we cannot control the conditions and circumstances of product transportation, storage and application and numerous other factors that affect its use. Thus, we shall not bear responsibility for the damage caused by ignoring the instructions for use or transportation, by noncompliance with storage conditions and timeframes or by inappropriate application of the product. The manufacturer reserves the right to alter product information at their discretion without prior notice. For additional information, please contact us: http://eskaro.ua/kontakty_ukr/	