












# TECHNICAL CHARACTERISTICS

## wineo 400 wineo

Heterogeneous resilient-flooring to glue - Covering type according to EN ISO 10582






	<b>wineo 400 wood</b>	<b>wineo 400 wood XL</b>	<b>wineo 400 stone</b>	
<b>Format</b>	1200 x 180 mm	1505 x 235 mm	609.6 x 304.8 mm	
<b>Product thickness</b>	2 mm	2 mm	2 mm	
<b>Planks, tiles / m<sup>2</sup> per box</b>	18 / 3.89 m <sup>2</sup>	12 / 4.24 m <sup>2</sup>	18 / 3.34 m <sup>2</sup>	
<b>Boxes / m<sup>2</sup> per pallet</b>	60 / 233.40 m <sup>2</sup>	64 / 271.36 m <sup>2</sup>	60 / 200.40 m <sup>2</sup>	
<b>Guarantee</b>	15 years for private use according to Windmüller warranty conditions – www.wineo.de			

Classification			Product composition	
	<b>Utilization class 23</b> EN ISO 10874	Heavy-duty use in the domestic area	1	<b>Surface sealing</b>
	<b>Utilization class 31</b> EN ISO 10874	Medium use in the commercial sector	2	<b>Surface texture</b> Various embossings
	Wear layer binder content EN ISO 10582	Type I	3	<b>Wear layer</b> Thickness 0.3 mm
	<b>R9</b> Anti slip category DIN 51130	R 9	4	<b>Decor</b> Decor film
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time	5	<b>Base layer</b>
	Light fastness EN ISO 105-B02	Light fastness (method 2) ≥ 6	6	<b>Backing</b>
	Residual indentation EN ISO 24343-1	≤ 0.1 mm without insulation mat ~ 0.17 mm with insulation mat silentPREMIUM		DESIGN Flooring to glue 
	Thermal resistance EN 12667	0.011 (m <sup>2</sup> K)/W without insulation mat 0,021 (m <sup>2</sup> K)/W with insulation mat silentPREMIUM		wood – bevelled edge - 4-sides wood XL – registered embossed surface, bevelled edge – 4-sides
	Impact sound reduction EN ISO 16251-1	~ 4 dB		
	Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203		

**CE** - 18 -


Windmüller GmbH  
Nord-West-Ring 21  
D-32832 Augustdorf

DOP: 0301010  
EN 14041:2004 / AC2006  
1658

www.wineo.de

**ÉMISSIONS DANS L'AIR INTÉRIEUR\***



Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)

**TÜV PROFIT CERT**  
70 710 4061-6  
www.profitcert.com

tested for emissions, harmful substances  
**PREMIUM**

**factory made coated**

Phthalat frei 100% Phthalat frei

- Relevant information:**
- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
  - Cleaning and care: see separate cleaning & care instruction.
  - Technical subjects can be changed by Windmüller GmbH.