

a. Multi-layer vinyl surface with PUR coating






b. Elastic damping layer

c. Special rigid polymer base board – waterproof








**Tests**
**DIN/EN standard**
**Edition M5**
**General data on product composition**

Type of covering:	Semi-rigid multi-layer flooring panel with an abrasion-resistant decorative top layer
Total thickness:	approx. 4.5 mm
Effective measurement: (length × width)	1,290 x 228 mm
Product structure:	a. Multi-layer vinyl surface (wear layer 0.55 mm) with PUR coating b. Elastic damping layer c. Special rigid polymer base board – waterproof

**Technical data**

Locking method:		Multiclic
 Wear class:	ISO 10 874	23   33
		
 Determination of personal voltage:	EN 1815	personal voltage $U_p < 2$ kV
 Wear resistance:	EN 15 468 (procedure B)	$IP \geq 5,000$ cycles
 Impact resistance:	EN 13 329 (appendix F)	$\geq 1,600$ mm
 Stain resistance:	EN 438-2/25	Group 1: grade 5 Group 2: grade 5 Group 3: grade 4 Coloured rubber, natural rubber or plastic glides and castors as well as dark car, bike or equipment tyres may possibly cause discolouration on flooring. Please only use light, non-migrating furniture glides, castors or tyres, if possible.
 Colour fastness:	EN ISO 105	$\geq$ stage 6 on the bluewool scale
 Fire behaviour:	EN 13 501	Bfl-s1 (hardly flammable)
 Slip resistance:	EN 14 041 / 13 893	DS

## Technical data

	Formaldehyde emissions (E1 = 0,1 ppm):	EN 717-1	target values met
	Indent after constant load:	EN ISO 24343-1	≤ 0.05 mm
	Castor resistance:	EN 425	no visible changes or damage with soft, standard castors (type W)
	Behaviour on simulation of shifting furniture foot:	EN 424	no visible damage
	Dimensional change due to change in temperature	EN ISO 23999	< 0.10 %
	Underfloor heating:		Suitable for hot-water underfloor heating Electrical underfloor heating is generally suitable when it is built into the floor screed or the concrete layer and thus does not lie on the concrete layer as foil heating. The heating elements   pipes   wires must lie across the entire area and not just be partly present. If the area is only partially heated, the floor covering must have expansion joints (system profile strips). The maximum permitted surface temperature is 29°C. Standard foil heating systems are generally not recommended. One exception is self-regulating heating systems which maintain the 29°C surface temperature.
	Heat transfer resistance:	EN 12 667	0,03 m² K/W with MEISTER-Silence 15 DB: 0,04 m² K/W
	Footfall noise reduction:	DIN EN ISO 10140-3	with MEISTER-Silence 15 DB: 16dB
	Antislip:	DIN 51 130 BGR 181	R9

## Tolerances

	Right-angle of the elements:	EN 16 511	target values met
	Determination of edge straightness:	EN 16 511	target values met
	Surface flushness:	EN 16 511	target values met
	Joint opening between the elements:	EN 16 511	target values met

## General data on environment, installation and care

Disposal:		Dispose residual pieces / large quantities according to municipal provisions (e.g. recycling centres)
Cleaning and care:		Cleaning after completion of construction work: CC PU Cleaner Day-to-day cleaning: CC PU Cleaner Freshening care: CC Floor Mat
Areas of application:		The flooring Edition M5 is suitable for all living areas as well as for commercial areas with heavy wear, e.g. open-plan offices, department stores, public buildings etc. This flooring is suitable for installation in humid/wet areas (according to Class A0, e.g. bathrooms). This flooring is not suitable for installation in outdoor areas, as well as in showers, public washrooms and saunas. Special requirements apply to treatment rooms and medical practices.
Preconditions for installation:	DIN 18 365	The laying surfaces must be considered to be ready for laying according to the generally recognised rules of the trade observing VOB, Part C, DIN 18 365 "Floor covering work". The laying surface must be dry (with a residual moisture of max. 2% for mineral subfloors or 1.8% with underfloor heating, or max. 0.5% for anhydrite screed or 0.3% with underfloor heating – measured using CM equipment), even, solid and clean. Furthermore, any unevenness of 3 mm per initial metre and 2 mm for each subsequent running metre must be evened out in accordance with DIN 18 202, Table 3, Row 4. We recommend consulting the technical information sheet 02 from the „Zentralverband für Parkett und Fußbodentechnik“ (Central Association for Parquet Flooring and Flooring Technology) and the BEB (Federal Association of Screed and Floor Covering). The system-oriented MEISTER insulating underlay Silence 15 DB with a pressure stability of > 200 kPa (CS value) is required for floating installation. Other types of insulating underlay must meet the increased requirements in accordance with the technical bulletin "TM 1" from MMFA for Class 2 floor coverings. The installation instructions provided with the product must be observed. For the installation a special 5mm tapping block is necessary.



MeisterWerke Schulte GmbH reserves the right to make alterations to material and structures when this serves to improve the quality.