

| Dimensions (l×b×h) in mm | International labeling | Weight |
|-----------------------------|---------------------------|-------------|
| 250x250x40 | ST40 | 5,5 kg/pc |
| | | |
| 300x150x30 | ST30 | 2,7 kg/pc |
| | | |
| 300x200x20 | ST30 | 2,4 kg/pc |
| 300x200x25 | ST30 | 3,2 kg/pc |
| 300x200x30 | ST30 | 3,6 kg/pc |
| | | |
| 320x290x15 | ST40 | 3,0 kg/pc |
| | | |
| 350x200x30 | ST30 | 4,4 kg/pc |
| 350x325x40 | ST30 | 9,6 kg/pc |
| 350x325x50 | ST30 | 12,0 kg/pc |
| | | |
| 400x200x20 | ST30 | 3,4 kg/pc |
| 400x200x25 | ST30 | 4,2 kg/pc |
| 400x200x30 | ST30 | 5,1 kg/pc |
| 400x200x30 | ST40 | 5,1 kg/pc |
| 400x200x40 | ST30 | 6,9 kg/pc |
| 400x200x50 | ST30 | 8,6 kg/pc |
| | | |
| 400x250x20 | ST30 | 4,2 kg/pc |
| 400x250x30 | ST30 | 6,3 kg/pc |
| | | |
| 400x300x20 | ST40 | 5,1 kg/pc |
| 400x300x25 | ST30 | 6,3 kg/pc |
| 400x300x30 | ST35 | 7,6 kg/pc |
| 400x300x30 | ST40 | 8,0 kg/pc |
| 400x300x40 | ST30 | 9,6 kg/pc |
| 400x300x40 | ST40 | 10,3 kg/pc |
| 400x300x50 | ST30 | 12,60 kg/pc |
| 400x300x50 | ST40 | 13,10 kg/pc |
| | | |
| 500x150x30 | ST30 | 4,8 kg/pc |
| | | |
| 500x200x20 | ST30 | 4,2 kg/pc |
| 500x200x30 | ST30 | 6,3 kg/pc |

| | | |
|------------|------|------------|
| 500x200x40 | ST30 | 8,4 kg/pc |
| | | |
| 500x250x20 | ST40 | 5,3 kg/pc |
| 500x250x25 | ST30 | 6,5 kg/pc |
| 500x250x30 | ST35 | 7,7 kg/pc |
| 500x250x40 | ST30 | 10,5 kg/pc |
| 500x250x50 | ST30 | 12,8 kg/pc |
| 500x250x64 | SP28 | 16,5 kg/pc |
| 500x250x64 | ST40 | 17,1 kg/pc |
| | | |
| 500x300x30 | ST35 | 9,5 kg/pc |
| 500x300x40 | ST30 | 12,6 kg/pc |
| 500x300x50 | ST30 | 15,8 kg/pc |
| 500x300x64 | ST30 | 20,2 kg/pc |
| | | |
| 500x375x30 | ST30 | 11,9 kg/pc |
| 500x375x40 | ST30 | 15,8 kg/pc |
| 500x375x64 | ST40 | 26,5 kg/pc |
| | | |
| 500x500x40 | ST30 | 21,0 kg/pc |
| 500x500x50 | ST30 | 26,3 kg/pc |
| | | |
| 600x300x20 | ST40 | 7,8 kg/pc |
| 600x300x25 | ST30 | 9,7 kg/pc |
| 600x300x30 | ST35 | 11,6 kg/pc |
| 600x300x40 | ST30 | 15,5 kg/pc |
| 600x300x60 | ST30 | 22,7 kg/pc |

Identification marking of refractory bricks:

| a | b | c |
|----|----|---|
| ST | 40 | K |

a. ST – high dense fire-clay

SP – dense fire-clay

b. 40 – content of Al₂O₃ in %

c. K – Acid proof

Dimensional tolerances:

| Grade | Dimension ≤ 150 mm | Dimension > 150 mm |
|--------|--------------------|--------------------|
| ST, SP | ± 2,0 mm | ± 1,5 % |