

**SGQ
SIAT S.p.A.**

1. DESCRIPTION

Gas shielded welding wire conforming to standard ISO 14341 A G 2Mo and AWS A5.28 ER70S-A1 suitable to join common steels and Mo low alloy steel for construction, pressure vessels and pipes. Particularly suitable to join steels resistant to hot creep up to 500°C and for tack weld in pipe production. Available in copper coated wire, standard and "Innov-Arc", and in no-copper wire, "Green-Arc".

2. PRODUCT CHEMICAL COMPOSITION (%)

		C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Al	V	Ti + Zr
PITTARC GMo	Min	0.08	0.90	0.30	-	-	-	-	0.40	-	-	-	-
	Max	0.12	1.30	0.70	0.020	0.020	0.15	0.15	0.60	0.35	0,02	0.03	0.15
ISO 14341-A G 2Mo	Min	0.08	0.90	0.30	-	-	-	-	0.40	-	-	-	-
	Max	0.12	1.30	0.70	0.020	0.020	0.15	0.15	0.60	0.35	0,02	0.03	0.15
AWS A5.28 ER70S-A1	Min	-	-	0.30	-	-	-	-	0.40	-	-	-	-
	Max	0.12	1.30	0.70	0.025	0.025	-	0.20	0.65	0.35	-	-	-

3. WIRE DIMENSIONS

Standard diameter (mm): 0.8; 1.0; 1.2; 1.4; 1.6
Permissible deviations: ISO 544

4. CAST AND HELIX (STANDARD PACKAGING)

Cast (mm): 800 ÷ 1000
Helix (mm): maximum 10

5. ALL-WELD-METAL MECHANICAL PROPERTIES

	Re MPa	Rm MPa	A5 %	KV (-40°C) J
AWS A5.28 ER70S-A1	≥ 400	≥ 515	≥ 19	-
ISO 14341-A-G46 4 M21 2Mo	≥ 460	≥ 530	≥ 20	≥ 47
ISO 14341-A-G50 4 M21 2Mo	≥ 500	≥ 560	≥ 18	≥ 47
PITTARC GMo	≥ 400	≥ 515	≥ 19	≥ 47

Gas protection: ISO 14175 M21 mixture (80% Ar + 20% CO₂). Preheating and interpass: < 200 °C.

Classification: ISO 14341-A- G 46 4 M21 2Mo, ISO 14341-A- G 50 4 M21 2Mo


6. STANDARD PACKAGING

Wire basket rim RG (ISO 544 B300) of 18 kg net weight. Each spool sealed in a polyethylene airtight bag and packed into a cardboard box. 72 spools stacked onto a pallet secured by thermoplastic shrink-wrapping (94x125x80 cm, 1296kg net weight). Available cardboard drums of about 250kg net weight, each one stacked onto a pallet 105x105x90 cm of about 1000kg total weight, secured by thermoplastic shrink-wrapping. On request packaging available from 15 kg up to 700 kg.

7. STANDARD IDENTIFICATION



A label is attached to the inside of each spool containing nominal diameter, trade name, classification, heat number, operator code. A label is attached to every box containing manufacturer, trade name, nominal diameter, heat number, spool type,


All data/information of this document are only at informative title and not binding for SIAT S.p.A., who entitles full right to modify/change them without prior notice.



**SGQ
SIAT S.p.A.**

references to the standards, CE mark and approvals.

 PITTARC	SIAT S.p.A. 33013 Gemona del Friuli (UD) ITALY			
 0036 06 ref. DoP PITTARC GMo-2020-10 EN 13479:2017 Use in metallic structures or in composite metal and concrete structures	PITTARC GMo			
	Welding wire for carbon steels and fine-grained steels EN ISO 14341-A – G46/50 4 M21 2Mo and AWS A5.28 ER70S-A1			
	Shielding gas according to ISO 14175 M21 Current/Polarity G + , Welding positions: PA-PB-PC-PD-PE-PF-PG			
	Weight kg	Heat N°	Diameter	Spool type
	XX	XXXXX/XX	X,X mm	X XXX



8. STANDARD CERTIFICATION

Documents according to EN 10204.

9. APPROVALS

None.