

PITTARC S4

SCP
SIAT

Descrizione/Description

Filo per saldatura in arco sommerso (SAW) di acciaio al carbonio non legati per recipienti a pressione, cantieristica navale e acciai strutturali.

Wire electrode for submerged arc welding (SAW) of mild steels used in pressure vessel, shipbuilding and structural steels.

Classificazione/Classification

EN ISO 14171-A S4
AWS A5.17/A5.23 EH14

Composizione chimica del filo/Wire electrode chemical composition

| | | C% | Mn% | Si% |
|----------------------|-----|------|------|------|
| PITTARC S4 | min | 0,10 | 1,75 | |
| | max | 0,15 | 2,20 | 0,10 |
| ISO 14171-A-S4 | min | 0,07 | 1,75 | |
| | max | 0,15 | 2,25 | 0,15 |
| AWS A5.17/A5.23-EH14 | min | 0,10 | 1,70 | |
| | max | 0,20 | 2,20 | 0,10 |

Per maggiori informazioni riguardanti le combinazioni prego vedere le schede tecniche del flusso.
For more information concerning the flux and wire combinations, please refer to the technical data sheet of the flux.

Approvazioni/Approvals

DB, TÜV / Marcatura CE - CE Marking

Per ulteriori informazioni relative al filo S4 vedere la scheda prodotto di riferimento Doc. SPP122.
For further information concerning the wire type S4 refer to the product data sheet Doc. SPP122.

All data/information of this document are only at informative title and not binding for SIAT S.p.A., who entitles full right to modify/change them without prior notice.

