

PITTARC S2Ni2

SGQ
SIAT S.p.A.

1. DESCRIPTION

Submerged arc welding wire conforming standards ISO 14171-A- S2Ni2 and AWS A5.23 ENi2 suitable to join Ni low alloy steels.

2. PRODUCT CHEMICAL COMPOSITION (%)

		C %	Mn %	Si %	P %	S %	Cr %	Ni %	Mo %	Cu %	Al %
Pittarc S2Ni2	min	0.07	0.90	0.05	-	-	-	2.10	-	-	-
	max	0.11	1.15	0.25	0.010	0.010	0.10	2.40	0.10	0.15	0.01
EN 14171-A-S2Ni2	min	0.07	0.80	0.05	-	-	-	1.80	-	-	-
	max	0.15	1.30	0.25	0.020	0.020	0.15	2.40	0.15	0.30	-
AWS A5.23 ENi2	min	-	0.75	0.05	-	-	-	2.10	-	-	-
	max	0.12	1.25	0.30	0.020	0.020	-	2.90	-	0.35	-

3. WIRE DIMENSIONS



Standard diameter (mm): 1.6; 2.0; 2.4; 3.2; 4.0; 4.8
Permissible deviations: ISO 544

4. STANDARD PACKAGING

Wire basket rim LC (ISO 544 B450) of 27kg net weight. Each spool sealed in a polyethylene airtight bag and packed into a cardboard box. 42 spools stacked onto a pallet secured by thermoplastic shrink-wrapping (120 x 80 cm, 1134kg net weight). Available cardboard drums of about 320kg net weight, each one stacked onto a pallet 110x110cm of about 1280kg total weight (4 drums), secured by thermoplastic shrink-wrapping. On request packaging available from 15 kg up to 900 kg.

5. STANDARD IDENTIFICATION

A label is attached to the inside of each spool or drums and to every box or outside of the drums mentioning manufacturer, trade name, nominal diameter, spool type, net weight, heat number, standards, CE mark and approvals.

 PITTARC	SIAT S.p.A. 33013 Gemona del Friuli (UD) ITALY		
 0036 06 ref. DoP PITTARC S2Ni2-2020-10 EN 13479:2017 Use in metallic structures or in composite metal and concrete structures	PITTARC S2Ni2		
	Welding wire for carbon steels and fine-grained steels ISO 14171 -A- S2Ni2 and AWS A5.23 ENi2		
	APPROVALS: TÜV Nr.07172		
	Weight kg	Heat N°	Diameter
	XX	XXXXX/XX	X,X mm
			Spool type
			X XXX

6. STANDARD CERTIFICATION

Documents according to EN 10204.

7. APPROVALS

TÜV.

