

PITTARC S3Ni1Mo0,2

SGQ
SIAT S.p.A.

1. DESCRIPTION

Submerged arc welding wire conforming standards ISO 14171-A- S3Ni1Mo0,2 and AWS A5.23 ENi5 suitable to join Mo low alloy steels for construction, pressure vessels, pipes.

2. PRODUCT CHEMICAL COMPOSITION (%)

		C %	Mn %	Si %	P %	S %	Cr %	Ni %	Mo %	Cu %	Al %
Pittarc S3Ni1Mo0,2	min	0.08	1.30	0.15	-	-	-	0.80	0.15	-	-
	max	0.12	1.60	0.30	0.015	0.015	0.15	1.00	0.30	0.15	0.02
EN 14171-A-S3Ni1Mo0,2	min	0.07	1.20	0.10	-	-	-	0.80	0.15	-	-
	max	0.15	1.60	0.35	0.015	0.015	0.15	1.20	0.30	0.30	-
AWS A5.23 ENi5	min	-	1.20	0.05	-	-	-	0.75	0.10	-	-
	max	0.12	1.60	0.30	0.020	0.020	-	1.25	0.30	0.35	-

3. WIRE DIMENSIONS



Standard diameter (mm): 1.6; 2.0; 2.4; 3.2; 4.0; 4.8
Permissible deviations: ISO 544

4. STANDARD PACKAGING

Wire basket rim LC (ISO 544 B450) of 27kg net weight. Each spool sealed in a polyethylene airtight bag and packed into a cardboard box. 42 spools stacked onto a pallet secured by thermoplastic shrink-wrapping (120 x 80 cm, 1134kg net weight). Available cardboard drums of about 320kg net weight, each one stacked onto a pallet 110x110cm of about 1280kg total weight (4 drums), secured by thermoplastic shrink-wrapping. On request packaging available from 15 kg up to 900 kg.

5. STANDARD IDENTIFICATION

A label is attached to the inside of each spool or drums and to every box or outside of the drums mentioning manufacturer, trade name, nominal diameter, spool type, net weight, heat number, standards, CE mark and approvals.

 PITTARC	SIAT S.p.A. 33013 Gemona del Friuli (UD) ITALY			
	PITTARC S3Ni1Mo0,2			
 0036 06 ref. DoP PITTARC S3Ni1Mo0,2-2019-03 EN 13479:2017 Use in metallic structures or in composite metal and concrete structures	Welding wire for carbon steels and fine-grained steels ISO 14171 -A- S3Ni1Mo0,2 and AWS A5.23 ENi5			
	APPROVALS: TÜV Nr.07172			
	Weight kg	Heat N°	Diameter	Spool type
	XX	XXXXX/XX	X,X mm	X XXX

6. STANDARD CERTIFICATION

Documents according to EN 10204.

7. APPROVALS

TÜV.

