

AURICOR 301N

GOLD PEN PLATING SOLUTION READY TO USE

Colour : **Yellow 1N-14**

Use : **Pen**

Colour coordinates : **L:90.4**

a:0.6

b:35.5

Product description

AURICOR 301N is an gold pen plating solution totally heavy metals free, suitable to deposit a layer of yellow gold with a color 1N-14k.

Operating conditions

Parameter	Average suggested value
Deposition time	5 - 10 seconds
Temperature	Room temperature
Voltage	7 V for brown tips - 9 V for white tips - 4 V for white buffer

Maintenance of plating bath

AURICOR 301N is to be used until exhausted.

Safety Information

Please refer to the safety data sheets for any information regarding safety and disposal (MSDS).

AURICOR 301N

GOLD PEN PLATING SOLUTION READY TO USE

Colour : **Yellow 1N**Use : **Pen**Colour coordinates : **L:90.4****a:0.6****b:35.5****Products related**

Cod.Articles	Description	Colour	Packaging
OR027601	AURICOR 301N gold pen plating solution 10 g/l	1N	100 ml