


TECHNICAL CHARACTERISTICS












wineo 800

Heterogeneous resilient-flooring to glue - Covering type according to EN ISO 10582

wineo

	wineo 800 wood	wineo 800 wood XL	wineo 800 stone XL	wineo 800 tile L / XL / XXL	wineo 800 craft
					
Format	1200 x 180mm	1505 x 235 mm	914.4 x 457.2 mm	457.2 x 457.2 mm 914.4 x 457.2 mm 914.4 x 914.4 mm	457.2 x 457.2 mm 914.4 x 101.6 mm
Product thickness	2.5 mm	2.5 mm	2.5 mm	2.5 mm	2.5 mm
Planks, tiles / m² per box	16 / 3.46 m ²	12 / 4.24 m ²	10 / 4.18 m ²	16 / 3.34 m ² 10 / 4.18 m ² 6 / 5.02 m ²	16 / 3.34 m ² 20 / 1.86 m ²
Boxes / m² per pallet	75 / 259.50 m ²	60 / 254.40 m ²	40 / 167.20 m ²	52 / 173.68 m ² 40 / 167.20 m ² 37 / 185.74 m ²	52 / 173.68 m ² 135 / 251.10 m ²
Guarantee	25 years for private use according to Windmüller warranty conditions - www.wineo.de				
Extended warranty	+ 5 years for laying on PU underlay mat				



Classification		Product composition
 Utilization class 23 EN ISO 10874	Domestic area with intensive usage	1 Surface seal
 Utilization class 33 EN ISO 10874	Commercial sector with heavy usage	2 Surface texture Various embossings
 Utilization class 42 EN ISO 10874	Light industry sector with regular usage	3 Wear layer Thickness 0.55 mm
Wear layer binder content EN ISO 10582	Typ I	4 Design Decor film
 R10 Anti slip category DIN 51130	R 10	5 Base layer
 Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time	6 Backing
 Light fastness EN ISO 105-B02	Light fastness (procedure 2) ≥ 6	7 Underlay material silentPREMIUM or silentPLUS (available separately)
 Residual indentation EN ISO 24343-1	≤ 0.1 mm without underlay mat ~ 0.17 mm with silentPREMIUM ~ 0.2 mm with silentPLUS	wood bevelled edge tile bevelled edge
 Castor chair test ISO 4918	25000 revolutions no damage with rolls type W	
 Thermal resistance EN 12667	≤ 0.015 (m ² K)/W without underlay mat ≤ 0.025 (m ² K)/W with silentPREMIUM or silentPLUS	
 Impact sound reduction EN ISO 16251-1	~ 4 dB without underlay mat ~ 17 dB with silentPREMIUM or silentPLUS	
 Dimensional stability EN ISO 23999	~ 0.15 %	
REACH	free from SVHC substances ≥ 0.1 %	
Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203	



CE - 18 -

Windmüller GmbH
Nord-West-Ring 21
D-32832 Augustdorf

DOP: 0301010
EN 14041:2004 / AC2006
1658

www.wineo.de

ÉMISSIONS DANS L'AIR INTÉRIEUR*

 **A+**

A+ A B C

Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)

phthalat frei  **factory made coated**

Relevant information:

- Utilization class 42 is not possible in conjunction with silentPREMIUM or silentPLUS.
- R 10 Decor „Heavy Metal“ excluded.
- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.