



TECHNICAL DATA SHEET No 510

## F 290 MULTIFILLER

### GENERAL TECHNICAL DESCRIPTION

Two component ultra lightweight polyester filler.

Absolute adhesion to all new galvanized substrates and all metallic surfaces.

Smooth spreading without pinholes.

Superb filling properties even on larger areas.

Effortless sanding.

### SURFACE

Metallic surfaces

- Aluminium
- Stainless steel
- Galvanised steel
- Bare metal

Wooden Surfaces

Polyester Surfaces

### PRETREATMENT/CLEANING OF SUBSTRATE



Sand surface with an appropriate grit paper



Clean substrate using a soft cloth and 770 ANTISIL NORMAL / 771 ANTISIL FAST DEGREASER.

Make sure the surface is first wiped dry and then air dried.

**PRODUCT APPLICATION: Apply with a spatula when mixed with hardener directly on surfaces to treat.**



Mix 100 parts FILLER with 2 - 3 parts BPO PASTE HARDENER



Apply with the spatula before it starts hardening  
Pot life: 4 - 5 min / 23°C (73°F)



Non force dry  
20 - 30 min / 23°C (73°F)



Short wave 5 – 8 min  
Lamp distance: 60 - 70 cm



P 120 – P 320



Paint over with HB BODY acrylic primers

### FLASH POINT

31°C / 88°F

### SPECIFIC GRAVITY

1.20 g/cm<sup>3</sup>

### SOLID CONTENT

(NO THINNER / REDUCER)

82% Weight

### VOC (2004/42/EC)

This is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 250 g/L. The VOC content in the ready for use form of this product is 250 g/L.

2004/42/II(b)(250)250

### THEORETICAL COVERAGE

-

### CLEANING OF EQUIPMENT

Clean after final use with 767 NITRO THINNER

### REMARKS

- Application only with BPO Paste Hardener. Mix well with putty. Do not add more than 3% as this may cause staining of the topcoat finish.
- Do not apply to Etch Primer, Wash Primer, 1K Filler, TPA substrates and soft old paintwork.
- Do not apply at temperatures below +5°C (+41°F).
- Dry sanding is always recommended.

### STORAGE SHELF LIFE

Polyester materials have a limited shelf life. Guaranteed shelf-life 18 months in unused original containers stored in a cool place (+5°C - +25°C) (41°F - 77°F).



Store in a cool place



Always wear protective equipment



Follow the application instructions mentioned in this TDS

**BPO Paste Hardener contains organic peroxide and is an oxidant. If hardener comes in contact with the skin, wipe off immediately and wash with soap and water. After eye contact irrigate copiously with water and seek medical advice immediately.**

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

DECEMBER 2022