

TECHNICAL DATA SHEET

Revision date: 15.02.2023

PLASTIC PRIMER

- Article number:** 26014
- Colour:** transparent
- Intended use:** Car refinishing product/ Preparation
- General characteristics:** High quality, fast drying plastic primer to treat surfaces, treated and untreated, of several types of plastic.
- Quality and properties:**
 - Fast drying
 - Excellent adhesion
 - Re-sprayable with all lacquer systems

Physical and chemical characteristics:

Base: Polyolefine resin
VOC-content: Approximately 99 % w/w
Solid content: Approximately 1 % w/w

Application process:

Before use, carefully read the directions on the packaging and act accordingly

Pre treatment:

The surface should be clean, dry and free of grease. When desired, slightly sand the surface, grain 600.

Treatment:

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 cm.

| Spraying operations | DFT | Consumption |
|---------------------|-----|----------------------|
| max. 2 thin layers | - | 2 - 3 m ² |

| Flash-off time | Between the coatings | Before the oven drying |
|----------------|----------------------|------------------------|
| | 2 - 3 min. | - |

■ **Processing conditions:**

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

| Drying | Dust dry | Recoatable |
|--------|----------|--------------|
| | - | 10 - 15 min. |

After use:

After drying, without sanding, re-sprayable with all lacquer systems. After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical data sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety data sheet.