

MOTIP Primer

Ord.-no.: look at ordering information

Technical Information



Use MOTIP Primer as a pre-treatment for painting your car. The primer is fast-drying and suitable for both treated and untreated surfaces including wood, metal, aluminium, glass and stone. The primer offers excellent coverage and filling properties and prevents rust. It is easy to sand, both wet and dry (from grain 400) and can be resprayed with all paints. MOTIP Primer is available in various colours.

Quality & properties

- Excellent coverage and filling property
- Easy to sand, both wet and dry (from grain 400)
- Corrosion preventive
- Re-sprayable with all lacquer systems
- Fast drying

Physical & chemical data

- Base:
 - ◊ Acrylic resin
 - ◊ Nitrocombi resin
- Colourname:
 - ◊ grey
 - ◊ black
 - ◊ beige yellow
 - ◊ red
 - ◊ white
- Smell: Characteristic
- Degree of gloss: mat, 10 ±2 GU
- Efficiency:
 - ◊ 500 ML – 1.5 - 2 m²
 - ◊ 500 ML – 1.5 - 2 m²
 - ◊ 150 ML – 0.5 m²
- Dry to touch:
 - ◊ 10 -20 min
 - ◊ 10 - 20 min
- Dust dry:
 - ◊ 5-10 min
 - ◊ 5 - 10 min
- Completely dry: 120 min
- Overcoatable: 120 min
- Surfaces: Wood, metal, aluminium, stone
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 25 °C
- Vapour pressure:
 - ◊ 3500/20 bar
 - ◊ 13/20 bar
 - ◊ 8300/20 bar
- Flash point: 27 °C
- Temperature Resistance: – 110 °C
- Storage stability:
 - ◊ 10 y
 - ◊ 5 y
 - ◊ 1.5 y
- Content:
 - ◊ 500 ML
 - ◊ 12 ML
 - ◊ 150 ML

How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- Pre Treatment: The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and

sand the surface.

- Treatment: The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 10 to 25°C.
- Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.
- Apply the primer in several thin layers. Before applying the next layer, again shake the aerosol.
- After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).
- The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labeling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of August 17, 2022 – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim - info-de@european-aerosols.com
European Aerosols B.V., Wolframweg 2, NL-8471 XC Wolvega - info-nl@european-aerosols.com