

Technical Datasheet

PRIMER PVC/TPO

Adhesion promoter of ISOFLEX-PU liquid waterproofing membranes to PVC or TPO membranes

Description

PRIMER PVC/TPO is a fast-acting, low viscosity, one-component, solvent-based adhesion promoter.

Fields of application

The PRIMER PVC/TPO (FPO) is well-suited to ensure the adhesion of ISOFLEX-PU polyurethane liquid waterproofing membranes when applied to existing surfaces waterproofed with PVC or TPO membranes.

Technical data

Form:	liquid
Color:	translucent
Density:	0.9 ± 0.05 kg/l

Directions for use

The existing PVC/TPO membranes should be previously cleaned with the special solvent SM-28. After cleaning, the membranes must be completely dry, clean, free of grease, loose particles, dust, etc. PRIMER PVC/TPO is applied with a roller in one layer. 20-30 minutes after the application – when the surface of the applied primer is dry and tack-free (depending on the weather conditions, such as wind, humidity and temperature) – the appropriate ISOFLEX-PU polyurethane liquid waterproofing membrane can be applied. Consumption approx. 100 g/m².

Packaging

PRIMER PVC/TPO is supplied in 4 kg tin buckets.

Shelf life – Storage

12 months from date of production if stored in original, sealed packaging, in areas protected from humidity and direct sunlight.

Recommended storage temperature between +5°C and +35°C.

Remarks

Temperature during the application and hardening of the product should be between +5°C and +35°C.

ISOMAT S.A.
BUILDING CHEMICALS, MORTARS & PAINTS
HEADQUARTERS – THESSALONIKI, GREECE
17th km Thessaloniki – Ag. Athanasios Road
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
T +30 2310 576000
www.isomat.eu e-mail: support@isomat.eu