



TIKKURILA

PONTTI FLOOR LACQUER 5

DEEP-MATT TINTABLE WATER-BORNE LACQUER FOR WOODEN FLOORS

- DESCRIPTION** Water-borne tintable polyurethane acrylate lacquer for interior use.
- RECOMMENDED USES** Top and maintenance lacquering of sanded interior wood surfaces. Test the product on a small area first to ensure that it is suitable for the surface. Also applies for varnishing the floors of summer apartments.
- PRODUCT FEATURES** Wooden floors and other interior wood surfaces subjected to light mechanical and chemical stress for residential buildings.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

PONTTI FLOOR LACQUER 5

TECHNICAL DATA	
Base paints	EP BASE
Colour Shades	Color cards: Interior wood stains and lacquers colour card, Tikkurila Timeless Translucent Can be tinted in Tikkurila translucent colors. Use Parketti-Ässä Petsi Stain for large surfaces to make an even end result. Spread the stain on bare wood.
Gloss	Full matt. full matt
Coverage	8-12 m ² /l.
Can sizes	0.9 l, 2.7 l, 9 l
Thinner	Water
Application method	Brush, roller
Drying time	Dust dry in approx. 1 hr. Recoatable after 4- 8 hours. Ready for use the following day. The lacquered surface will reach its final hardness after approx. two weeks. Avoid hard stresses, cleaning and placing of sticking and heavy objects on the lacquered surface during this time.
Density (kg/l)	1,03 kg/l, ISO 2811
Volume solids (%)	30
Weight solids (%)	29
VOC	(cat A/i) 140g/l(2010) Pontti Floor Lacquer 5 contains VOC max. 140 g/l.
Storage	Protect from frost.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



PONTTI FLOOR LACQUER 5

APPLICATION INSTRUCTIONS

Application conditions

The wooden surface must be dry and free of any dirt, wax or grease. The temperature of the air and surface should be at least +10°C, and the relative humidity of the air 30–80%.

Surface preparation

Bare wooden surfaces:

Clean the floor from dirt, wax and grease. Moisten the surface lightly with water, let dry and sand off the loose wood fibers. Remove the sanding dust.

Previously lacquered wooden surfaces:

Wash previously painted surfaces with Maalipesu Cleaning Agent. Let it dry. Sand the surface matt (sanding paper no 120 or 150). Remove sanding dust carefully with a vacuum cleaner and wipe the surface with a damp, lint-free and clean cloth. If the lacquered surface is in very poor condition, remove the lacquer completely with a paint remover or by sanding. Before lacquering, check the suitability of Pontti Floor Lacquer 5 on previously treated floors by lacquering a small test area.

Lacquering

Bare wooden surfaces:

Stir Pontti lacquer thoroughly down to the bottom before and occasionally during use. Color large untreated wooden surfaces with Parketti-Ässä Petsi. Tinted Pontti Floor Lacquer 5 is suitable for small surfaces like previously lacquered stairs or thresholds. Apply lacquer to wooden boards lengthwise few boards at a time. Apply the lacquer slowly and gently, avoid rotating/abrasive movements. Handle the surface 2-3 times.

Previously lacquered wooden surfaces:

Stir Pontti lacquer thoroughly down to the bottom before and occasionally during use. Apply lacquer to wooden boards lengthwise few boards at a time. Apply the lacquer slowly and gently, avoid rotating/abrasive movements. Handle the surface 1-2 times.

Note

Tinting instruction: Choose the colour from Tikkurila translucent colours collection. Remove the lid, tint product, close the can.

Cleaning of tools

Clean tools with water or Tikkurila Pensselipesu (Tool Cleaner). Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Maintenance instructions

The lacquered surface reaches its final wear and chemical resistance in approximately two weeks from the surface treatment. Avoid cleaning the floor during this time. Clean the surface with a brush, mop or dust cloth. Dirty surfaces can be cleaned with a cleaning tool and a neutral (pH 6–8) washing solution.

Environmental protection and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

Health and Safety

The product is not classified as hazardous according to Regulation (EC) 1272/2008 as amended. Wear protective gloves. Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains: C(M)IT/MIT (3:1) and BIT.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.