

AKDRY Zr OCTOATE 6%

Description : Zirconium Octoate, an auxiliary siccative.

Specifications;

Density (@20°C) : 0,83 ± 0,01 gr/cm³
Viscosity(@20°C) : 0,5 - 1,5 mPas
Appearance : Transparent Liquid
Diluent : WS
Metal Content : 5,9 - 6,1 %
Solid Content : 15 ± 2 %
Color : Colorless
CAS No. : 22464-99-9; 64742-81-0
EINECS/ELINCS No. : 245-018-1; 265-184-9
UN No. : 1993

Application : Miscible with organic solvents and oils. Zirconium Octoate siccatives particularly recommended in order to prevent ecologic disadvantages of Lead driers.

Usage & Amount : Zirconium Octoate is generally used with Cobalt siccatives in order to obtain a hard and durable film layer. Suitable to be used instead of Lead driers. Recommended amount is 75% of Lead Octoate.

Packaging : 50 Kgs PE Pail, 180 Kgs Barrel

Handling & Storage : Recommended storage temperature is between +5 °C and +40 °C. Keep pails tightly closed. Store and handle in a dry, well-ventilated place. Keep away from sources of heat, ignition and direct sunlight in original packaging. Provide grounding and venting in order to prevent static electricity build-up. Avoid any contact with Organic Peroxides.

Shelf Life : 1 Year
For unopened packages at recommended storage conditions.