



 Made in Italy

Marvel Travertine Pearl Cross 120x120 Matt Sensitech

Толщина 9 mm Эффект камня Мраморный эффект Эффект травертина

Код товара: #a8ww

Основные характеристики



Толщина:
9 mm




Barefoot
ramp test:
R10, A+B



V-Shade:
V3

Сертификаты



Мир

MARVELWORLD

Technologies

 **Sensitech**

Техническая информация

Regularity Carachteristics



ISO 10545-2

Length and width: Suitable for
Толщина: Suitable for
Straightness of sides: Suitable for
Perpendicularity: Suitable for



ISO 10545-2

Surface Flatness: Suitable for

Structural Carachteristics



ISO 10545-3

Water Absorption (in % by mass): $\leq 0.1\%$



ASTM C373-18

Water Absorption (in % by mass): $\leq 0.5\%$

Bulk Mechanical Carachteristics



ISO 10545-4

Breaking strenght: $S \geq 1500$ N
Bending resistance: $R \geq 40$ N/mm²



ISO 10545-5

Impact resistance, as coefficient of restitution: ≥ 0.55

Surface Mechanical Carachteristics



ISO 10545-6

Resistance to deep abrasion of unglazed tiles (removed volume): ≤ 150 mm³

Thermo-Hygrometric Carachteristics



10545-8

Coefficient of thermal linear expansion: ≤ 7 MK⁻¹



10545-9

Thermal shock resistance: Resistant



10545-10

Moisture expansion (in mm/m): $\leq 0.01\%$ (0.1mm/m)



10545-12

Frost resistance: Resistant

Физические свойства



Bond strength/adhesion for improved cementitious adhesives

Bond strength/adhesion for improved cementitious adhesives: ≥ 1.0 N/mm² (Class C2 - EN 12004)



Reaction to fire: A1 - A1fl

Chemical Caratteristiche



ISO 10545-13

Resistance to household chemicals and swimming pool salts: A
Resistance to low concentration of acids and alkalis: LA
Resistance to high concentrations of acids and alkalis: HA



ISO 10545-14

Stain resistance: 5

Safety Caratteristiche



DIN EN 16165 ANNEX B (EX DIN 51130)

Booted ramp test: R10



DIN EN 16165 ANNEX A (EX DIN 51097)

Barefoot ramp test: A+B



BS EN 16165 ANNEX C (EX BS 7976)

Pendulum friction Test: ≥ 36 Dry ≥ 36 Wet



AS 4586

Pendulum friction Test: Class P3



UNE 41901 (EX:2017)

Pendulum friction Test: Class C2



B.C.R.A. Rep. CEC/81

Coefficient of friction (COF)-
: >0.40 Asciutto >0.40 Bagnato



ANSI A 326,3

Dynamic coefficient of friction (DCOF):
Wet DCOF ≥ 0.50