


LR6-72 **330~350W**

High Reliability, Production Efficiency and High Power Output

LONGi Solar mono solar cell modules have higher reliability. The highest power output can be 350W. They have excellent performance even under the low - temperature or low - light environment. We promise to provide high-efficiency, high power output Mono-crystalline silicon products, thus guarantee the return on investment.



Complete System and Product Certifications

IEC 61215, IEC 61730, JET, CQC, CE

ISO 9001: 2008: ISO Quality Management System ISO 14001: 2004: ISO Environment Management System OHSAS 18001: 2007 Occupational Health and Safety













^{*}Specifications subject to technical changes and tests. LONGi Solar reserves the right of final interpretation.

Positive Power Tolerance

0~+5W positive tolerance of maximal power guaranteed.

High Conversion Efficiency

The highest efficiency up to 18.1%.

Excellent Performance in Low irradiance

Outstanding power output in low irradiance conditions, such as dawn, duskand cloudy days.

Anti-PID

Anti-PID techniques of processing solar cells and encapsulating modules applied; adaptable for the installation in hot and highly humid areas.

Adaptability to the Harsh Environments

Excellent anti salt mist and anti-ammonia capability and is adaptable to the harsh environments, such as seaside and farms.

Super Robust Frame, 40mm Thickness

Good pressure resistance and able to bear2400Pa wind load and 5400Pa snow load.



Room 201, Building 8, Sandhill Plaza, Lane 2290, Zuchongzhi Road, Pudong New District, Shanghai, 201203 Tel: 86-21-61047332 Fax: 86-21-61047377 Email: module@longi-silicon.com

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.

LR6-72 **330~350W**

Mechanical Detail (mm) **Mechanical Parameters Operating Parameters** Number of Cells: 72 (6×12) Operating Temperature: -40°C \sim +85°C Junction Box: IP67, three diodes Power Tolerance: 0~+5W Output Cable: 4mm², 1000mm in length Maximum System Voltage(V): DC1000V (IEC) Connector: MC4 or compatible with MC4 Maximum Series Fuse Rating: 15A NOCT: 45°C±2°C Weight: 22.5kg Dimension: 1956×991×40mm Application Class: Class A Packaging: 26pcs per pallet


Туре	LR6-7	2-330M	LR6-7	2-335M	LR6-72	2-340M	LR6-7	2-345M	LR6-7	2-350M
Testing Condition	SSTC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT
Maximum Power (Pmax/W)	330	238.6	335	242.2	340	245.8	345	249.4	350	253.0
Open Circuit Voltage (Voc/V)	46.1	42.4	46.3	42.6	46.5	42.8	46.7	43	46.9	43.1
Short Circuit Current (Isc /A)	9.30	7.50	9.40	7.58	9.49	7.65	9.58	7.72	9.68	7.80
Voltage at Maximum Power (Vmp/V)	37.6	34.0	37.7	34.1	37.9	34.2	38.1	34.5	38.2	34.6
Current at Maximum Power (Imp /A)	8.78	7.02	8.89	7.11	8.97	7.18	9.05	7.24	9.16	7.32
Module Efficiency (%)	17.0	1	17.3	/	17.5	1	17.8	/	18.1	/


NOCT (Nominal Operating Cell Temperature): Irradiance 800W/m², Ambient Temperature 20°C, Spectra at AM1.5, Wind at 1m/S


991±1 (39±0.04)

Temp. Coefficient (STC	Testing)	Load					
Temperature Coefficient of Isc	+0.059%/°C	Maximum Front Static Load (Snow)	5400pa				
Temperature Coefficient of Voc	-0.330%/°C	Maximum Rear Static Load (Wind)	2400pa				
Temperature Coefficient of Pmax	-0.410% / °C	Pass the Hailstone Test	25mm Hailstone at the speed of 23m/s				

I-VCurve









Room 201, Building 8, Sandhill Plaza, Lane 2290, Zuchongzhi Road, Pudong New District, Shanghai, 201203 Tel: 86-21-61047332 Fax: 86-21-61047377 Email: module@longi-silicon.com

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.